

N120N

Technical Data Sheet

N120N

Nonwoven Geotextile for Drainage and Separation

N120N is a polypropylene, needle punched nonwoven geotextile for use in drainage and separation applications. It has been stabilized to resist degradation due to ultraviolet exposure and is resistant to commonly encountered mildew, insects and soil chemicals, and is non-biodegradable. Polypropylene is stable with a pH range of 2 to 13.

| Geotextile Property | Test Method | Minimum Average Roll Values |
|-----------------------------------|-------------|--------------------------------|
| Grab Tensile Strength | ASTM D4632 | 300 Lbs |
| Grab Tensile Elongation | ASTM D4632 | 50 % |
| CBR Puncture Strength | ASTM D6241 | 800 Lbs |
| Trapezoid Tear Strength | ASTM D4533 | 115 Lbs |
| UV Resistance @ 500 Hours | ASTM D4355 | 70 % |
| AOS | ASTM D4751 | 100 Sieve |
| Permittivity (sec ⁻¹) | ASTM D4491 | 0.8 sec ⁻¹ |
| Flow Rate | ASTM D4491 | 65 gpm/ft ² |

Results quoted above are the mean of multiple tests conducted at an independent testing facility. N120N meets or exceeds values listed.

Packaging

 Roll Width
 12.5 ft.
 15 ft.

 Roll Length
 300 ft.
 300 ft.

 Roll Area
 417 sy
 500 sy



09 2024

Disclaimer: Ferguson/ACF Environmental assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information

Ferguson Enterprises, LLC dba ACF Environmental
2831 Cardwell Road, Richmond, VA 23234
Contact infogeo@ferguson.com or visit us at www.fergusongss.com