

## **ACF 1515BX**

## **BX Series**

## **Technical Data Sheet**

## Biaxial Geogrid for Paving and Reinforcement

ACF 1515BX geogrid is composed of polypropylene resin which is extruded into a stable geogrid structure. ACF 1515BX geogrid is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

ACF 1515BX geogrid increases roadbed and foundation bearing capacity, while prolonging the service life of each by the confinement of the base course. ACF 1515BX prevents lateral spreading of the base or sub-base aggregate and allows for shear interaction to develop between the aggregate and the geogrid.

ACF 1515BX geogrid reduces the applied vertical pressure of heavy loads at depth of aggregate by spreading the load over a wider area

Geogrid Property	Test Method	Typical Roll Value	
		<u>MD</u>	<u>CD</u>
Ultimate Tensile Strength <sup>1</sup>	ASTM D6637	1030 lbs/ft	1030 lbs/ft
Tensile Strength @ 2%1	ASTM D6637	340 lbs/ft	340 lbs/ft
Tensile Strength @ 5%1	ASTM D6637	750 lbs/ft	750 lbs/ft
UV Resistance	ASTM D4355	100%	
Junction Efficiency <sup>2</sup>	ASTM D7737	93%	
Flexural Stiffness <sup>3</sup>		325,000 mg-cm	
Aperture Stability <sup>4</sup>		0.38 m-N/deg	
Resistance to UV Degradation <sup>5</sup>	ASTM D4355	100%	
Rib Thickness		0.035 in	0.025 in
Aperture Size		1.5 in	1.5 in
Roll Size (width x length)		12.5 ft x 328 ft	
Roll Area		456 yds <sup>2</sup>	

<sup>&</sup>lt;sup>1</sup>True resistance to elongation when initially subjected to a load determined in accordance with ASTM D 6637 without deforming test materials under load before measuring such resistance or employing "secant" or "offset" tangent methods of measurement so as to overstate tensile properties.

Disclaimer: Ferguson/ACF Environmental assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information.

<sup>&</sup>lt;sup>2</sup>Load transfer capability calculated as a % of ultimate tensile strength.

<sup>&</sup>lt;sup>3</sup>Resistance to bending force determined in accordance with ASTM D 7748/7748M-14.

<sup>&</sup>lt;sup>4</sup>Resistance to in-plane rotational movement measured by applying a 20kg-cm (2 m-N) moment to the central junction of a 9 inch x 9 inch specimen in accordance with U.S. Army Corps of Engineers Methodology for measurement of Torsional Rigidity.

<sup>&</sup>lt;sup>5</sup>Tested according to ASTM D 4355.