

ACF M100

Woven Geotextile for Filtration

ACF M100 is manufactured using high tenacity monofilament polypropylene yarns woven to form a dimensionally stable network. It has been stabilized to resist degradation due to ultraviolet exposure and is resistant to commonly encountered mildew, insects and soil chemicals, and is non-biodegradable. The high strength of ACF M100 makes it ideal for filtration beneath hard armor applications. Polypropylene is stable with a pH range of 2 to 13.

Geotextile Property	Test Method	Minimum Average Roll Values
Grab Tensile Strength	ASTM D4632	370 x 250 Lbs
Grab Tensile Elongation	ASTM D4632	15 %
CBR Puncture Strength	ASTM D6241	950 Lbs
Trapezoid Tear Strength	ASTM D4533	100 x 60 Lbs
UV Resistance @ 500 Hours	ASTM D4355	90 %
AOS	ASTM D4751	70 Sieve
Percent Open Area	COE-02215	4 %
Permittivity (sec ⁻¹)	ASTM D4491	0.28 sec ⁻¹
Flow Rate	ASTM D4491	18 gpm/ft ²

Results quoted above are the mean of multiple tests conducted at an independent testing facility. ACF M100 meets or exceeds values listed.

Packaging

Roll Width	6 ft.	12 ft.
Roll Length	300 ft.	300 ft.
Roll Area	200 sy	400 sy

11 2024

Disclaimer: Ferguson/ACF Environmental assumes no liability for the completeness or accuracy of this information or the ultimate use of this information. This document should not be construed as engineering advice. Always consult the project engineer for project specific requirements. The end user assumes sole responsibility for the use of this information